



**CYCLE GROUP**

**“EcoGranule™” QD**

**Technical Specifications**

**Component Composition: Wood Fiber + Granite + Binder**

**Properties**

**Product Description: 12/40 QD**

**Bulk Density (ASTM E 727) : 39 - 44 pounds per cubic foot**

**Moisture Content: < 2%**

**pH: 6 - 8**

**Angle of Repose: < 39 degrees**

**Liquid Holding Capacity: > 15%**

**Resistance to Attrition (ASTM E 728): > 92%**

**Screen Analysis (US Mesh Sizes):**

**+ #12 < 5% (Target = 2.5%)**

**- #12 to + #40 > 92%**

**- #40 < 3%**

**Effective Date: June 8, 2010**