



## Heavy Weight 20/50 “EcoGranule™”

### Technical Specifications

#### Component Composition

Hardwood fibers

Granite

Binder

#### Products Properties

##### *20/50 mesh*

Screen Analysis	+16 mesh <1% 20 to 50 mesh 90% -60 mesh <1%		
Bulk Density	40-44 lbs/cft	ASTM	E 727 - 02
Resistance to Attrition	>90%	ASTM	E 728 - 97
Moisture Content	<2 %		
pH	6 -7		
Angle of repose	39°	ISO 8398/ EN 12047 – 96 (1)	
Liquid Holding Capacity	18% - 20%	ASTM	E 1521 - 98
Visual dust	2-4 seconds		Internal procedure (2)