



## **EcoGranule® 5/12 HW**

### Technical Specifications

#### **Component Composition**

Wood Fiber  
Granite and/or dolomite  
Binder

#### **Products Properties**

##### ***5/12 mesh***

Screen Analysis	+5 mesh <5% 5 to 12 mesh >90% -12 mesh <5%		
Bulk Density	40-44 lbs/cft	ASTM	E 727 - 02
Resistance to Attrition	>90%	ASTM	E 728 - 97
Moisture Content	<4 %		
pH	6 -7		
Angle of repose	39°	ISO 8398/ EN 12047 – 96	(1)
Liquid Holding Capacity	15%	ASTM	E 1521 - 98
Visual dust	2-3 seconds	Internal procedure	(2)